





Fathum



Juice Box





Black

Sea Mist



Blueberry



Chocolate



Construction	Values Test Method			
Surface Composition	100% Polyurethane			
Backing Composition	100% Polyester	ASTM D 751-89		
Finished Width	54" min.	ASTM D 751-89		
Repeat	None			
Railroaded	No			
Put-up	30 yards			
Cleaning Code	W/S			
Performance	Values	Test Method		
Grab Tensile	80 lbs./in.× 70 lbs./in. min.	ASTM D 5034-09		
Trap Tear	15 lbs./in. × 15 lbs./in. min.	ASTM D 5587-07		
Seam Strength	60 lbs./in. × 60 lbs./in. min.	ASTM D 1683-07A		
Adhesion	4 lbs./in. × 4 lbs./in. min.	ASTM D 751-89		
Stretch @ 15# (MD×CD)	2 % ×7%	ASTM D 751-89		
Flex Resistance	50,000 cycles	ASTM D 2097-03		
Blocking	No. 1 - Pass	Fed. Std. 191 A , 5872		
Crock Resistance	Dry-4; Wet-4	AATCC 8-2013		
Wyzenbeek Abrasion	100,000 cycles, #10 Cotton Duck	ASTM D 4157-07		
Hydrolysis Resistance	24 weeks ISO 1419: 1995 E			
UV Stability	200 hours	AATCC 16-2004		
Blue Dye Transfer Resistance	Dry-4-5; Wet-4-5	LP-463KC-04-03		

California Technical Bulletin 117-2013, Sec. 1	Pass
IMO A.652(16)8.2	Pass
NFPA 260	Pass
ILEAC Class I	Pass

Environmental

- 1. No anti-microbial additives
- 2. Does not contain PFAS, PFOA
- 3. Prop 65 compliant
- 4. No chemical flame retardants, CA AB2998 compliant

5. REACH, RoHS, and LEED compliant

Suitable Applications Contract, Healthcare, Hospitality, Residential

Cleaning and Disinfecting

Remove ordinary dirt and smudges with mild soap and water. A 10:1 ratio of water to bleach solution may be used as a disinfectant. Rinse the surface with clean water after disinfecting. Dry with a soft, lint-free cloth or towel. We recommend that you use Clorox Healthcare and Clorox Pro products to disinfect Mitchell products in commercial settings.



