



Values

**Test Method** 



Construction

Construction	values	iesi memod
Surface Composition	100% Polyurethane	
Backing Composition	100% Polyester	ASTM D 751-89
Finished Width	54" min.	ASTM D 751-89
Repeat	None	
Railroaded	No	
Put-up	30 yards	
Cleaning Code	W/S	
Performance	Values	Test Method
Grab Tensile	80 lbs./in.× 70 lbs./in. min.	ASTM D 5034-09
Trap Tear	15 lbs./in. × 15 lbs./in. min.	ASTM D 5587-07
Seam Strength	60 lbs./in. × 60 lbs./in. min.	ASTM D 1683-07A
Adhesion	4 lbs./in. × 4 lbs./in. min.	ASTM D 751-89
Stretch @ 15# (MD×CD)	2 % ×7%	ASTM D 751-89
Flex Resistance	50,000 cycles	ASTM D 2097-03
Blocking	No. 1 - Pass	Fed. Std. 191 A, 5872
Crock Resistance	Dry - 4; Wet - 4	AATCC 8-2013
Wyzenbeek Abrasion (#10 Cotton Duck)	100,000 cycles	ASTM D 4157-07
Hydrolysis Resistance	24 weeks	ISO 1419: 1995 E
UV Stability	200 hours	AATCC 16-2004
Blue Dye Transfer Resistance	Dry-4-5; Wet-4-5	LP-463KC-04-03

California Technical Bulletin 117-2013, Sec. 1	Pass
IMO A.652(16)8.2	Pass
NFPA 260	Pass
U.F.A.C. Class I	Pass

## **Environmental**

- 1. No anti-microbial additives
- 2. Does not contain PFAS, PFOA
- 3. Prop 65 compliant
- 4. No chemical flame retardants, CA AB2998 compliant
- 5. REACH, RoHS, and LEED compliant

Suitable Applications Contract, Healthcare, Hospitality, Residential

## **Cleaning and Disinfecting**

Remove ordinary dirt and smudges with mild soap and water. A 10:1 ratio of water to bleach solution may be used as a disinfectant. Rinse the surface with clean water after disinfecting. Dry with a soft, lint-free cloth or towel. We recommend that you use Clorox Healthcare and Clorox Pro products to disinfect Mitchell products in commercial settings.



