



Moss



Construction	Values	Test Method
Surface Composition	100% Polyurethane	
Backing Composition	100% Polyester	ASTM D 751-06
Finished Width	54" min.	ASTM D 751-06
Repeat	None	
Railroaded	No	
Put-up	30 yards	
Cleaning Code	W/S	
Stain Resistant	Yes	
Performance	Values	Test Method
Grab Tensile	80 lbs./in.× 80 lbs./in.	ASTM D 751-06
Trap Tear	15 lbs./in. × 15 lbs./in.	ASTM D 751-06
Seam Strength	40 lbs./in. × 40 lbs./in.	ASTM D 751-06
Adhesion	4 lbs./in. × 4 lbs./in	ASTM D 751-06
Stretch @ 15# MD (warp) ×CD (fill)	2% × 7%	ASTM D 751-06
Flex Resistance	25,000 cycles	ASTM D 2097-91
Blocking	No. 1 - Pass	Fed. Std. 191 A , 5872
Crock Resistance	Dry-4; Wet-4	AATCC 8-2007
Wyzenbeek Abrasion	300,000 cycles, #10 Cotton Duck	ASTM D 4157-07 ISO
Hydrolysis Resistance	24 weeks	1419: 1995
Colorfastness to Light	200 hours	ASTM D 4329-05
Blue Dye Transfer Resistance	Dry-4-5; Wet-4-5	LP-463KC-04-03
Anti-Bacterial	Pass	AATCC 147-2004
Mildew Resistance	Pass	ASTM G-21

## **Flammability**

Cold Crack (#5 roller)

California Technical Bulletin 117-2013, Sec. 1

IMO A.652(16)8.2

Pass
2. Does not contain PFAS, PFOA

NFPA 260

Pass
3. Prop 65 compliant

U.F.A.C. Class I

Pass
4. No chemical flame retardants, CA AB2998 compliant

5. REACH, RoHS, and LEED compliant

**Environmental** 

Suitable Applications Contract, Healthcare, Hospitality, Residential

-20°F

## **Cleaning and Disinfecting**

Remove ordinary dirt and smudges with mild soap and water. A 10:1 ratio of water to bleach solution may be used as a disinfectant. Rinse the surface with clean water after disinfecting. Dry with a soft, lint-free cloth or towel. We recommend that you use Clorox Healthcare and Clorox Pro products to disinfect Mitchell products in commercial settings.





CFFA-6A