





Construction	Values			Test Method	
Surface Composition	100% Polyurethane				
Backing Composition	100% Polyester			ASTM D 751-06	
Finished Width	54" min.			ASTM D 751-06	
Repeat	None				
Railroaded	No				
Put-up	30 yards				
Cleaning Code	W/S				
Stain Resistant	Yes				
Performance	Values			Test Method	
Grab Tensile	80 lbs./in.× 80 lbs./in.			ASTM D 751-06	
Trap Tear	15 lbs./in. × 15 lbs./in.			ASTM D 751-06	
Seam Strength	40 lbs./in. × 40 lbs./in.			ASTM D 751-06	
Adhesion	4 lbs./in. × 4 lbs./in			ASTM D 751-06	
Stretch @ 15# MD (warp) ×CD (fill)	2% × 7%			ASTM D 751-06	
Flex Resistance	25,000 cycles			ASTM D 2097-91	
Blocking	No. 1 - Pass			Fed. Std. 191 A , 5872	
Crock Resistance	Dry-4; Wet-4			AATCC 8-2007	
Wyzenbeek Abrasion	300,000 cycles, #10 Cotton Duck			ASTM D 4157-07	
Hydrolysis Resistance	24 weeks			ISO 1419: 1995 E	
Colorfastness to Light	200 hours			ASTM D 4329-05	
Blue Dye Transfer Resistance	Dry-4-5; Wet-4-5			LP-463KC-04-03	
Cold Crack (#5 roller)	-20°F			CFFA-6A	
Flammability			Environmental		
California Technical Bulletin 117-2013, Sec. 1 Pass			1. No anti-microbial additives		
IMO A.652(16)8.2 Pass			2. Does not contain PFAS, PFOA		
NFPA 260	PA 260 Pass			3. Prop 65 compliant	
U.F.A.C. Class I			4. No chemical flame retardants, CA AB2998 compliant		
			5. REACH, RoHS, o	and LEED compliant	

Suitable Applications Contract, Healthcare, Hospitality, Residential

## **Cleaning and Disinfecting**

Remove ordinary dirt and smudges with mild soap and water. A 10:1 ratio of water to bleach solution may be used as a disinfectant. Rinse the surface with clean water after disinfecting. Dry with a soft, lint-free cloth or towel. We recommend that you use Clorox Healthcare and Clorox Pro products to disinfect Mitchell products in commercial settings.



