





Construction	Values		Test Method
Surface Composition	100% Polyurethane		
Backing Composition	100% Polyester		ASTM D 751-06
Finished Width	54" min.		ASTM D 751-06
Repeat	None		
Railroaded	No		
Put-up	30 yards		
Cleaning Code	W/S		
Stain Resistant	Yes		
Performance	Values		Test Method
Grab Tensile	80 lbs./in.× 80 lbs./in.		ASTM D 751-06
Trap Tear	15 lbs./in. × 15 lbs./in.		ASTM D 751-06
Seam Strength	40 lbs./in. × 40 lbs./in.		ASTM D 751-06
Adhesion	4 lbs./in. × 4 lbs./in		ASTM D 751-06
Stretch @ 15# MD (warp) ×CD (fill)	2% × 7%		ASTM D 751-06
Flex Resistance	25,000 cycles		ASTM D 2097-91
Blocking	No. 1 - Pass		Fed. Std. 191 A, 5872
Crock Resistance	Dry - 4; Wet -4		AATCC 8-2007
Wyzenbeek Abrasion (#10 Cotton Duck)	300,000 cycles		ASTM D 4157-07
Hydrolysis Resistance	24 weeks		ISO 1419: 1995 E
Colorfastness to Light	200 hours		ASTM D 4329-05
Blue Dye Transfer Resistance	Dry - 4-5; Wet-4-5		LP-463KC-04-03
Cold Crack (#5 roller)	-20°F		CFFA-6A
Flammability		Environmental	
California Technical Bulletin 117-2013, Sec. 1 Pass		1. No anti-microbial additives	
IMO A.652(16)8.2	Pass	2. Does not contain PFAS, PFOA	
NFPA 260	Pass	3. Prop 65 complia	nt
U.F.A.C. Class I	Pass	4. No chemical flame retardants, CA AB2998 compliant	
		5. REACH, RoHS, an	nd LEED compliant

<u>Suitable Applications</u> Contract, Healthcare, Hospitality, Residential

## **Cleaning and Disinfecting**

Remove ordinary dirt and smudges with mild soap and water. A 10:1 ratio of water to bleach solution may be used as a disinfectant. Rinse the surface with clean water after disinfecting. Dry with a soft, lint-free cloth or towel. We recommend that you use Clorox Healthcare and Clorox Pro products to disinfect Mitchell products in commercial settings.



