







Black



Grey



Sand Surf



Golden Brown



Buff



Tangerine



Geranium

Navy



| Construction        | Values                           | Test Method   |  |  |
|---------------------|----------------------------------|---------------|--|--|
| Surface Composition | 100% Polyurethane                |               |  |  |
| Backing Composition | 100% Polyester                   | ASTM D 751-89 |  |  |
| Finished Width      | 54" min.                         | ASTM D 751-89 |  |  |
| Repeat              | None                             |               |  |  |
| Railroaded          | No                               |               |  |  |
| Put-up              | 30 yards                         |               |  |  |
| Cleaning Code       | W/S                              |               |  |  |
| Performance         | Values                           | Test Method   |  |  |
| Cuarla Tarrailla    | OF Heading woodless the resident | 4 CT          |  |  |

| remance                      | values                          | lest Method                 |
|------------------------------|---------------------------------|-----------------------------|
| Grab Tensile                 | 95 lbs./in.× 80 lbs./in. min.   | ASTM D 5035-09              |
| Trap Tear                    | 15 lbs./in. × 15 lbs./in. min.  | ASTM D 5587-07              |
| Seam Strength                | 40 lbs./in. × 35 lbs./in. min.  | ASTM D 1683-07A             |
| Adhesion                     | 4 lbs./in. × 4 lbs./in. min.    | ASTM D 751-89               |
| Stretch @ 15# (MD×CD)        | 2% × 12%                        | ASTM D 751-89               |
| Flex Resistance              | 25,000 Cycles                   | ASTM D 2097-91              |
| Blocking                     | No. 1 - Pass                    | Federal Standard 191A, 5304 |
| Crock Resistance             | Dry-4; Wet-4                    | Federal Standard 191A, 5651 |
| Wyzenbeek Abrasion           | 300,000 cycles, #10 Cotton Duck | ASTM D 4157-07              |
| Hydrolysis Resistance        | 7 weeks                         | ASTM D3690-02               |
| UV Stability                 | 1000 hours                      | AATCC 16-2004               |
| Blue Dye Transfer Resistance | Dry 4-5; Wet 4-5                | LP-463KC-04-03              |
| Anti-Bacterial               | Pass                            | ASTM E 1428-99              |
| Mildew Resistance            | Pass                            | ASTM G-21                   |
| Cold Crack                   | -20°F                           | CFFA-6A                     |
|                              |                                 |                             |

## Flammability Environmental

| California Technical Bulletin 117-2013, Sec. 1 | Pass | <ol> <li>No anti-microbial additives</li> </ol>      |
|--|------|--|
| IMO A.652(16)8.2                               | Pass | 2. Does not contain PFAS, PFOA                       |
| NFPA 260                                       | Pass | 3. Prop 65 compliant                                 |
| U.F.A.C. Class I                               | Pass | 4. No chemical flame retardants, CA AB2998 compliant |
|  |      | 5. REACH, RoHS, and LEED compliant                   |

Suitable Applications Contract, Healthcare, Hospitality, Residential

## **Cleaning and Disinfecting**

Remove ordinary dirt and smudges with mild soap and water. A 10:1 ratio of water to bleach solution may be used as a disinfectant. Rinse the surface with clean water after disinfecting. Dry with a soft, lint-free cloth or towel. We recommend that you use Clorox Healthcare and Clorox Pro products to disinfect Mitchell products in commercial settings.



