

White	lvory	Camel	Lipstick	Ocean	Pear
Pumice	Stone	Brick	Port	Sapphire	Pine
Jet	Charcoal	Bark	Raisin	Grotto	

sta*kleen. polyurethane

Product Specifications

Construction	Values			Test Method	
Surface Composition	100% Polyurethane		е		
Backing Composition	100% Polyester			ASTM D 751-06	
Finished Width	54" min.			ASTM D 751-06	
Repeat	None				
Railroaded	No				
Put-up	30 yards				
Cleaning Code	W/S				
Stain Resistant	Yes				
Performance	Values			Test Method	
Grab Tensile	80 lbs./in.× 80 lbs./in.		/in.	ASTM D 751-06	
Trap Tear	15 lbs./in. × 15 lbs./in.			ASTM D 751-06	
Seam Strength	40 lbs./in.	40 lbs./in. × 40 lbs./in.		ASTM D 751-06	
Adhesion	4 lbs./in. × 4 lbs./in		1	ASTM D 751-06	
Stretch @ 15# MD (warp) ×CD (fill)	2% × 7%			ASTM D 751-06	
Flex Resistance	25,000 cycles			ASTM D 2097-91	
Blocking	No. 1 - Pass			Fed. Std. 191 A , 5872	
Crock Resistance	Dry-4; Wet-4			AATCC 8-2007	
Wyzenbeek Abrasion	300,000 cycles, #10 Cotton Duck			ASTM D 4157-07	
Hydrolysis Resistance	24 weeks			ISO 1419: 1995	
Colorfastness to Light	200 hours			ASTM D 4329-05	
Blue Dye Transfer Resistance	Dry-4-5; Wet-4-5			LP-463KC-04-03	
Anti-Bacterial	Pass			AATCC 147-2004	
Mildew Resistance	Pass			ASTM G-21	
Cold Crack (#5 roller)	-20°F			CFFA-6A	
Flammability			Environmental		
California Technical Bulletin 117-2013, Sec. 1 Pass			1. No anti-microbial additives		
IMO A.652(16)8.2 Pass			2. Does not contain PFAS, PFOA		
NFPA 260		Pass	3. Prop 65 compliant		
U.F.A.C. Class I		Pass	4. No chemical flame retardants, CA AB2998 compliant		
			5. REACH, RoHS, and LEED compliant		

Suitable Applications Contract, Healthcare, Hospitality, Residential

Cleaning and Disinfecting

Remove ordinary dirt and smudges with mild soap and water. A 10:1 ratio of water to bleach solution may be used as a disinfectant. Rinse the surface with clean water after disinfecting. Dry with a soft, lint-free cloth or towel. We recommend that you use Clorox Healthcare and Clorox Pro products to disinfect Mitchell products in commercial settings.

