



Bark



Pumice



Charcoal



Raisin




Grotto




Sapphire









White



Pine

## **Product Specifications**

Tucson

Construction	Values		Test Method	
Surface Composition	100% Polyurethane			
Backing Composition	100% Polyester		ASTM D 751-06	
Finished Width	54" min.		ASTM D 751-06	
Repeat	None			
Railroaded	No			
Put-up	30 yards			
Cleaning Code	W/S			
Stain Resistant	Yes			
Performance	Values		Test Method	
Grab Tensile	80 lbs./in.× 80 lbs./in.		ASTM D 751-06	
Trap Tear	15 lbs./in. × 15 lbs./in.		ASTM D 751-06	
Seam Strength	40 lbs./in. × 40 lbs./in.		ASTM D 751-06	
Adhesion	4 lbs./in. × 4 lbs./in		ASTM D 751-06	
Stretch @ 15# MD (warp) ×CD (fill)	2% × 7%		ASTM D 751-06	
Flex Resistance	25,000 cycles		ASTM D 2097-91	
Blocking	No. 1 - Pass		Fed. Std. 191 A , 5872	
Crock Resistance	Dry-4; Wet-4		AATCC 8-2007	
Wyzenbeek Abrasion	300,000 cycles, #10 Cotton Duck		ASTM D 4157-07	
Hydrolysis Resistance	24 weeks		ISO 1419: 1995 E	
Colorfastness to Light	200 hours		ASTM D 4329-05	
Blue Dye Transfer Resistance	Dry-4-5; Wet-4-5		LP-463KC-04-03	
Cold Crack (#5 roller)	-20°F		CFFA-6A	
Flammability		Environmenta	l i i i i i i i i i i i i i i i i i i i	
California Technical Bulletin 117-2013, Sec. 1 Pass		1. No anti-micro	1. No anti-microbial additives	
IMO A.652(16)8.2 Pass		ss 2. Does not cor	2. Does not contain PFAS, PFOA	
NFPA 260 Pass		ss 3. Prop 65 com	3. Prop 65 compliant	
J.F.A.C. Class I			flame retardants, CA AB2998 compliant	
			, and LEED compliant	

Suitable Applications Contract, Healthcare, Hospitality, Residential

## **Cleaning and Disinfecting**

kleen

POLYURFTHANF

Remove ordinary dirt and smudges with mild soap and water. A 10:1 ratio of water to bleach solution may be used as a disinfectant. Rinse the surface with clean water after disinfecting. Dry with a soft, lint-free cloth or towel. We recommend that you use Clorox Healthcare and Clorox Pro products to disinfect Mitchell products in commercial settings.

