




Bark



Charcoal



Grotto




Jet




Ocean



Pine




Pumice




Raisin



Sapphire



Stone



White

Construction	Values	Test Method
Surface Composition	100% Polyurethane	
Backing Composition	100% Polyester	ASTM D 751-06
Finished Width	54" min.	ASTM D 751-06
Repeat	None	
Railroaded	No	
Put-up	30 yards	
Cleaning Code	W/S	
Stain Resistant	Yes	

Performance	Values	Test Method
Grab Tensile	80 lbs./in. × 80 lbs./in.	ASTM D 751-06
Trap Tear	15 lbs./in. × 15 lbs./in.	ASTM D 751-06
Seam Strength	40 lbs./in. × 40 lbs./in.	ASTM D 751-06
Adhesion	4 lbs./in. × 4 lbs./in.	ASTM D 751-06
Stretch @ 15# MD (warp) × CD (fill)	2% × 7%	ASTM D 751-06
Flex Resistance	25,000 cycles	ASTM D 2097-91
Blocking	No. 1 - Pass	Fed. Std. 191 A, 5872
Crock Resistance	Dry-4; Wet-4	AATCC 8-2007
Wyzenbeek Abrasion (#10 Cotton Duck)	300,000 cycles	ASTM D 4157-07
Hydrolysis Resistance	24 weeks	ISO 1419: 1995 E
Colorfastness to Light	200 hours	ASTM D 4329-05
Blue Dye Transfer Resistance	Dry-4-5; Wet-4-5	LP-463KC-04-03
Cold Crack (#5 roller)	-20°F	CFFA-6A

Flammability	Environmental
California Technical Bulletin 117-2013, Sec. 1	Pass 1. No anti-microbial additives
IMO A.652(16)8.2	Pass 2. Does not contain PFAS, PFOA
NFPA 260	Pass 3. Prop 65 compliant
U.F.A.C. Class I	Pass 4. No chemical flame retardants, CA AB2998 compliant
	5. REACH, RoHS, and LEED compliant

Suitable Applications Contract, Healthcare, Hospitality, Residential

Cleaning and Disinfecting

Remove ordinary dirt and smudges with mild soap and water. A 10:1 ratio of water to bleach solution may be used as a disinfectant. Rinse the surface with clean water after disinfecting. Dry with a soft, lint-free cloth or towel. We recommend that you use Clorox Healthcare and Clorox Pro products to disinfect Mitchell products in commercial settings.



The Mitchell Group is a compatibility partner with Clorox Healthcare

The Mitchell Group
7040 N. Austin Avenue | Niles, IL 60714
847.647.7300 | mitchellfauxleathers.com