



Product Specifications

Ez-Kleen - BIGHORN



Technical Specs

| | <u>Values</u> | <u>Test Method</u> |
|---------------------|----------------|--------------------|
| Surface Composition | PVC | ASTM D 751-06 |
| Finished Width | 54" min. | ASTM D 751-06 |
| Backing Composition | 100% Polyester | ASTM D 751-06 |
| Repeat | None | ASTM D 751-06 |
| Railroaded | No | |
| Put-up | 30 yards | |
| Cleaning Code | WS | |
| Protective Finish | Ez-Kleen™ | |

Performance

| | <u>Values</u> | <u>Test Method</u> |
|-----------------------------|----------------------------------|---------------------------------|
| Grab Tensile | 110 lbs./in. x 110 lbs./in. min. | ASTM D 751-06 |
| Trap Tear | 35 lbs./in. x 35 lbs./in. min. | ASTM D 751-06 |
| Seam Strength | 35 lbs./in. x 35 lbs./in. min. | ASTM D 751-06 |
| Adhesion | 4 lbs./in. x 4 lbs./in. min. | ASTM D 751-06 |
| Flex Resistance | 25,000 Cycles | ASTM D 2097-91 |
| Blocking | No. 1 - Pass | FTMS 191A-TM5872 |
| Wyzenbeek Abrasion | 100,000 cycles, #10 cotton duck | ASTM D 4157-13 |
| UV Stability | 250 hours, Grade 4-5 | ASTM D 4329-05 |
| Crock Resistance | Dry - 4-5; Wet - 4-5 | AATCC 8-2016 |
| Blue Jean Dye Transfer Test | Dry - 4-5; Wet - 4 | Chrysler Method: LP-463KC-04-03 |
| Stretch (MDxCD) | 7% x 30% | ASTM D 751-06 |

Flammability

| | |
|---|------|
| California Bulletin 117-2013, Section 1 | Pass |
| NFPA 260 | Pass |
| UFAC Class I | Pass |
| FMVSS/CMVSS #302 | Pass |
| IMO 2010, Part 8, Section 3.1 | Pass |

Environmental

Does not contain any flame retardant chemicals.

Does not contain anti-microbial additives

Phthalate free

RoHS compliant.

Suitable Applications: Contract, Healthcare, Hospitality, Residential