



Product Specifications

Mitchell Collection - CROCK



Technical Specs

	<u>Values</u>	<u>Test Method</u>
Surface Composition	100% PVC	
Backing Composition	65% Polyester / 35% Cotton	ASTM D 751-06
Finished Width	54" min.	ASTM D 751-06
Repeat	V: 10" / H: 10.75"	ASTM D 751-06
Railroaded	No	
Put-up	30 yards	
Cleaning Code	W	

Performance

	<u>Values</u>	<u>Test Method</u>
Grab Tensile	85 lbs./in. x 90 lbs./in. min.	ASTM D 751-06
Trap Tear	15 lbs./in. x 15lbs./in. min.	ASTM D 751-06
Seam Strength	65 lbs./in. x 65 lbs./in. min.	ASTM D 751-06
Adhesion	4 lbs./in. x 4 lbs./in. min.	ASTM D 751-06
Flex Resistance	25,000 Cycles	ASTM D 2097-03(2010)
Blocking	No. 1 - Pass	FTMS 191A-TM5872
Wyzenbeek Abrasion	35,000 cycles, #8 cotton duck	ASTM D 4157-92
UV Stability	40 hours (no color change)	ASTM D 4329-05
Crock Resistance	D-4; W-4	AATCC 8-2007
Stretch (MDxCD)	2% x 9% at 15 lbs.	ASTM D 751-06

Flammability

California Bulletin 117-2013, Section 1	Pass
U.F.A.C. Class I	Pass
NFPA 260	Pass

Environmental

7p Free - Does not contains the following phthalates: DBP, BBP, DEHP, DOP, DNOP, DINP, DIDP

Suitable Applications: Residential