



## Product Specifications

# Sta-Kleen® - HUDSON



### Technical Specs

Surface Composition	100% Polyurethane
Backing Composition	100% Polyester
Finished Width	54" min.
Put-up	30 yards
Repeat	None
Railroaded	No
Cleaning Code	W/S

### Test Method

ASTM D 751-89
ASTM D 751-89

### Performance

Grab Tensile	80 lbs./in. x 70 lbs./in. min.
Trap Tear	15 lbs./in. x 15 lbs./in. min.
Seam Strength	60 lbs./in. x 60 lbs./in. min.
Adhesion	4 lbs./in. x 4 lbs./in. min.
Stretch at 15# MD (warp) xCD (fill)	2 % x7%
Flex Resistance	50,000 cycles
Blocking	No. 1 - Pass
Crock Resistance	Dry-4; Wet-4
Wyzenbeek Abrasion	100,000 cycles, #10 Cotton Duck
Hydrolysis Resistance	10 weeks
UV Stability	200 hours
Blue Dye Transfer Resistance	Dry-4-5; Wet-4-5
Anti-Bacterial	No growth
Mildew Resistance	No growth

### Test Method

ASTM D 5034-09
ASTM D 5587-07
ASTM D 1683-07A
ASTM D 751-89
ASTM D 751-89
ASTM D 2097-03
Fed. Std. 191 A , 5872
AATCC 8-2013
ASTM D 4157-07
ISO 1419: 1995 E
AATCC 16-2004
LP-463KC-04-03
AATCC 147-2004
ASTM G-21

### Flammability

IMO A.652(16)8.2	Pass
California Bulletin 117-2013, Section 1	Pass
U.F.A.C. Class I	Pass
NFPA 260	Pass

### Environmental

Does not contain PFAS, PFOA or formaldehyde.



**Suitable Applications:** Hospitality, Contract, Healthcare, Residential