



Smoke



Aloe



Grey



Saddle Brown



Chocolate

Construction	Values	Test Method
Surface Composition	100% Polyurethane	
Backing Composition	95% Polyester, 5% Cotton	ASTM D 751-89
Finished Width	54" min.	ASTM D 751-89
Repeat	None	
Railroaded	No	
Put-up	30 yards	
Cleaning Code	W	

Performance	Minimum Values	Test Method
Grab Tensile	100 lbs./in. × 100 lbs./in. min.	ASTM D 5034-09
Trap Tear	15 lbs./in. × 15 lbs./in. min.	ASTM D 5587-07
Seam Strength	35 lbs./in. × 35 lbs./in. min.	ASTM D 1683-07A
Adhesion	3 lbs./in. × 3 lbs./in. min.	ASTM D 751-89
Stretch @ 15# (MD×CD)	2% × 2%	ASTM D 751-89
Flex Resistance	25,000 Cycles	ASTM D 2097-91
Blocking	No. 1 - Pass	Fed. Std. 191 A , 5872
Crock Resistance	20 cycles - Pass	Fed. Std. 191 A , 5651
Wyzenbeek Abrasion	25,000 cycles, #10 cotton duck	ASTM D 4157-07
Hydrolysis Resistance	3 weeks	ISO 5423: 1992 E
UV Stability	40 hours (Grade 4)	AATCC 16-2004

Flammability		Environmental
California Technical Bulletin 117-2013, Sec. 1	Pass	1. No anti-microbial additives
FMVSS & CMVSS 302	Pass	2. Does not contain PFAS, PFOA
NFPA 260	Pass	3. Prop 65 compliant
U.F.A.C. Class I	Pass	4. No chemical flame retardants, CA AB2998 compliant
		5. REACH, RoHS, and LEED compliant

Suitable Applications Residential, RV

Cleaning and Disinfecting

Remove ordinary dirt and smudges with mild soap and water. A 10:1 ratio of water to bleach solution may be used as a disinfectant. Rinse the surface with clean water after disinfecting. Dry with a soft, lint-free cloth or towel. We recommend that you use Clorox Healthcare and Clorox Pro products to disinfect Mitchell products in commercial settings.

