



Brindle




Taupe



Ash Grey



Saddle



Burly



Dark Chocolate

Construction

Surface Composition
 Backing Composition
 Finished Width
 Repeat
 Railroaded
 Put-up
 Cleaning Code

Values

100% Polyurethane
 65% Polyester / 35% Cotton
 54" min.
 None
 No
 30 yards
 W

Test Method

ASTM D 751-06
 ASTM D 751-06

Performance

Grab Tensile
 Trap Tear
 Seam Strength
 Adhesion
 Stretch @ 15# (MD×CD)
 Flex Resistance
 Blocking
 Crock Resistance
 Wyzenbeek Abrasion
 Hydrolysis Resistance
 UV Stability

Minimum Values

80 lbs./in. × 70 lbs./in. min.
 15 lbs./in. × 12 lbs./in. min.
 60 lbs./in. × 60 lbs./in. min.
 3 lbs./in. × 3 lbs./in. min.
 3% × 4%
 25,000 Cycles
 No. 1 - Pass
 Wet-4; Dry-4
 100,000 cycles, #8 cotton duck
 3 weeks
 40 hours

Test Method

ASTM D 751-06
 ASTM D 751-06
 ASTM D 751-06
 ASTM D 751-06
 ASTM D 751-06
 ASTM D 2097-03(2010)
 FTMS 191A-TM5872
 AATCC 8-2007
 ASTM D 4157-92
 ISO 5423: 1992cE
 ASTM D 4329-05

Flammability

California Technical Bulletin 117-2013, Sec. 1 Pass
 NFPA 260 Pass
 U.F.A.C. Class I Pass

Environmental

1. No anti-microbial additives
2. Does not contain PFAS, PFOA
3. Prop 65 compliant
4. No chemical flame retardants, CA AB2998 compliant
5. REACH, RoHS, and LEED compliant

Suitable Applications Residential

Cleaning and Disinfecting

Remove ordinary dirt and smudges with mild soap and water. A 10:1 ratio of water to bleach solution may be used as a disinfectant. Rinse the surface with clean water after disinfecting. Dry with a soft, lint-free cloth or towel. We recommend that you use Clorox Healthcare and Clorox Pro products to disinfect Mitchell products in commercial settings.

