



## Product Specifications

# Mitchell Collection - BODIE



### Technical Specs

	<u>Values</u>	<u>Test Method</u>
Surface Composition	100% Polyurethane	
Backing Composition	65% Polyester / 35% Cotton	ASTM D 751-06
Finished Width	54" min.	ASTM D 751-06
Repeat	None	
Railroaded	No	
Put-up	30 yards	
Cleaning Code	W	

### Performance

	<u>Values</u>	<u>Test Method</u>
Grab Tensile	80 lbs./in. x 70 lbs./in. min.	ASTM D 751-06
Trap Tear	15 lbs./in. x 12lbs./in. min.	ASTM D 751-06
Seam Strength	60 lbs./in. x 60 lbs./in. min.	ASTM D 751-06
Adhesion	3 lbs./in. x 3 lbs./in. min.	ASTM D 751-06
Stretch @ 15# (MDxCD)	3% x 4%	ASTM D 751-06
Flex Resistance	25,000 Cycles	ASTM D 2097-03(2010)
Blocking	No. 1 - Pass	FTMS 191A-TM5872
Crock Resistance	Dry-4; Wet-4	AATCC 8-2007
Wyzenbeek Abrasion	100,000 cycles, #8 cotton duck	ASTM D 4157-92
Hydrolysis Resistance	5 weeks	ASTM D 3690-02
UV Stability	40 hours (no color change)	ASTM D 4329-05

### Flammability

California Bulletin 117-2013, Section 1	Pass
U.F.A.C. Class I	Pass
NFPA 260	Pass

**Suitable Applications:** Commercial