



Product Specifications

Mitchell Collection - CHAPARRO



<u>Technical Specs</u>	<u>Values</u>	<u>Test Method</u>
Surface Composition	100% Polyurethane	
Backing Composition	100% Polyester	ASTM D 751-06
Finished Width	54" min.	ASTM D 751-06
Repeat	None	
Railroaded	No	
Put-up	30 yards	
Cleaning Code	W	

<u>Performance</u>	<u>Values</u>	<u>Test Method</u>
Grab Tensile	220 lbs./in. x 80 lbs./in. min.	ASTM D 5034-09
Trap Tear	60 lbs./in. x 35 lbs./in. min.	ASTM D 5587-07
Seam Strength	130 lbs./in. x 80 lbs./in. min.	ASTM D 1683-11a
Adhesion	3 lbs./in. x 3 lbs./in. min.	ASTM D 751-06
Stretch @ 15# (MDxCD)	2% x 5%	ASTM D 751-06
Flex Resistance	25,000 Cycles	ASTM D 2097-03(2010)
Blocking	No. 1 - Pass	FTMS 191A-TM5872
Crock Resistance	20 cycles - Pass	AATCC 8-2007
Wyzenbeek Abrasion	50,000 cycles, #10 Cotton Duck	ASTM D 4157-13
Hydrolysis Resistance	5 weeks	ASTM D 3690-02
UV Stability	40 hours (no color change)	ASTM D 4329-05

<u>Flammability</u>	
California Bulletin 117-2013, Section 1	Pass
U.F.A.C. - Class I	Pass
NFPA 260	Pass

Suitable Applications: Residential