



Product Specifications

Mitchell Collection - DORA



Technical Specs

Surface Composition	100% Polyurethane
Finished Width	54" min.
Backing Composition	100% Rayon
Put-up	30 yards
Repeat	None
Cleaning Code	W
Railroaded	No

Test Method

ASTM D 751-06
ASTM D 751-06

Performance

Grab Tensile	60 lbs./in. × 60 lbs./in. min.
Trap Tear	15 lbs./in. × 15 lbs./in. min.
Seam Strength	40 lbs./in. × 40 lbs./in. min.
Adhesion	4 lbs./in. × 4 lbs./in. min.
Stretch at 15# MD (warp) × CD (fill)	10% × 15%
Flex Resistance	25,000 cycles
Blocking	No. 1 - PASS
Wyzenbeek Abrasion	Pass - 100,000 cycles, #10 Cotton Duck
Hydrolysis Resistance	5 weeks
UV Stability	150 hours
Crock Resistance	Wet-4; Dry-4
Cold Crack (#5 roller)	-20°F

Test Method

ASTM D 751-06
ASTM D 751-06
ASTM D 751-06
ASTM D 751-06
ASTM D 751-06
ASTM D 2097-91
TM582
ASTM D 4157-13
ISO 1419: 1995
ASTM D 4329-05
AATCC 8-2007
CFFA-6A

Flammability

California TB117-2013	Pass
U.F.A.C. Class I	Pass
NFPA 260 Pass	Pass

Environmental

1. No chemical flame retardants
2. No persistent organic pollutants
3. No toxic by products

Cleaning and Disinfecting

Remove ordinary dirt and smudges with mild soap and water. A 10:1 ratio of water to bleach solution may be used as a disinfectant. Rinse the surface with clean water after disinfecting.

Dry with a soft, lint-free cloth or towel.