



## Product Specifications

# Mitchell Collection: Pacific



### Technical Specs

	<u>Values</u>	<u>Test Method</u>
Surface Composition	100% PVC	ASTM D 751-06
Backing Composition	100% Polyester	ASTM D 751-06
Finished Width	54" min.	ASTM D 751-06
Repeat	None	ASTM D 751-06
Railroaded	No	
Put-up	30 yards	
Cleaning Code	W	

### Performance

	<u>Values</u>	<u>Test Method</u>
Grab Tensile	80 lbs./in. x 100 lbs./in. min.	ASTM D 751-06
Trap Tear	20 lbs./in. x 20 lbs./in. min.	ASTM D 751-06
Seam Strength	50 lbs./in. x 50 lbs./in. min.	ASTM D 751-06
Adhesion	4 lbs./in. x 4 lbs./in. min.	ASTM D 751-06
Flex Resistance	25,000 Cycles	ASTM D 2097-91
Blocking	No. 1 - Pass	FTMS 191A-TM5872
Wyzenbeek Abrasion	100,000 cycles, #10 cotton duck	ASTM D 4157-13
UV Stability	650 hours	ASTM D 4329-05
Mildew Resistance	Pass - No growth	ASTM G-21
Crock Resistance	Dry - 4; Wet - 4	AATCC 8-2016
Stretch (MD x CD)	4% x 12%	ASTM D 751-06
Pink Stain	Pass - No growth	ASTM E 1428
Cold Crack	Pass -40°F	CFFA-6a

### Flammability

California Bulletin 117-2013, Section 1	Pass
NFPA 260	Pass
UFAC Class I	Pass
FMVSS/CMVSS #302	Pass
IMO 2010, Part 8, Section 3.1	Pass

**Suitable Applications:** Contract, Healthcare, Hospitality, Residential