



MITCHELL™
COLLECTION

CHAPARRO



Ashes



Gray Wolf



Sagebrush



Creek



Prairie



Trail Dust



Log Cabin



Dark Brown



Light Brown



Boot Straps



Reins

Technical Specifications	Values	Test Method
Surface Composition	100% Polyurethane	
Backing Composition	100% Polyester	ASTM D 751-06
Finished Width	54" min.	ASTM D 751-06
Repeat	None	
Railroaded	No	
Put-up	30 yards	
Cleaning Code	W	

Performance		Test Method
Grab Tensile	220 lbs./in. × 80 lbs./in. min.	ASTM D 5034-09
Trap Tear	60 lbs./in. × 35 lbs./in. min.	ASTM D 5587-07
Seam Strength	130 lbs./in. × 80 lbs./in. min	ASTM D 1683-11a
Adhesion	3 lbs./in. × 3 lbs./in. min.	ASTM D 751-06
Stretch @ 15# (MD×CD)	2% × 5%	ASTM D 751-06
Flex Resistance	25,000 Cycles	ASTM D 2097-03(2010)
Blocking	No. 1 - Pass	FTMS 191A-TM5872
Crock Resistance	20 cycles - Pass	AATCC 8-2007
Wyzenbeek Abrasion	50,000 cycles, #10 cotton duck	ASTM D 4157-13
Hydrolysis Resistance	5 weeks	ASTM D 3690-02
UV Stability	40 hours (no color change)	ASTM D 4329-05

Flammability	
California Bulletin 117-2013, Section 1	Pass
U.F.A.C. Class I	Pass
NFPA 260	Pass

Suitable Applications	Residential
-----------------------	-------------

Cleaning and Disinfecting

Remove ordinary dirt and smudges with mild soap and water. A 10:1 ratio of water to bleach solution may be used as a disinfectant. Rinse the surface with clean water after disinfecting. Dry with a soft, lint-free cloth or towel.