



Product Specifications

ReCast® - MONTANA



Technical Specs

	<u>Values</u>	<u>Test Method</u>
Surface Composition	100% Polyurethane	
Finished Width	54" min.	ASTM D 751-06
Weight at 54 inches	23.4 oz./yd.	ASTM D 751-06
Thickness	1.0 mm ±10%	ASTM D 751-06
Total Weight	15.6 oz./yd ² ±10%	ASTM D 751-06
Backing Composition	14% Cotton /28% Leather / 57% Polyester	ASTM D 751-06
Backing Weight	8.7 oz. / yd ² ±10%	ASTM D 751-06
Repeat	None	
Railroaded	N	
Put-up	30 yards	
Cleaning Code	W	

Performance

	<u>Values</u>	<u>Test Method</u>
Grab Tensile	80 lbs./in. × 60 lbs./in. min.	ASTM D 751-06
Trap Tear	15 lbs./in. × 15 lbs./in. min.	ASTM D 5733-99
Seam Strength	40 lbs./in. × 40 lbs./in. min.	ASTM D 751-06
Adhesion	4 lbs./in. × 4 lbs./in. min.	ASTM D 751-06
Stretch at 15# MD (warp) ×CD (fill)	5% × 10%	ASTM D 751-06
Flex Resistance	25,000 cycles	ASTM D 2097-91
Blocking	No. 1 - Pass	Fed. Std. 191 A, 5872
Crock Resistance	Dry-4; Wet-4	AATCC 8-2007
Wyzenbeek Abrasion	100,000 cycles, #10 Cotton Duck	ASTM D 4157-13
Hydrolysis Resistance	5 weeks	ASTM D 3690-02
UV Stability	200 hours	CFFA-6A

Flammability

California Bulletin 117-2013, Section 1	Pass
U.F.A.C. Class I	Pass
NFPA 260 Class 1	Pass

Suitable Applications: Commercial; Residential

Country of Origin: China

10/16/2015 - Revision: 6