



Product Specifications

Sta-Kleen® - PAYSON



<u>Technical Specs</u>	<u>Values</u>	<u>Test Method</u>
Surface Composition	100% Polyurethane	
Backing Composition	100% Polyester	ASTM D 751-06
Finished Width	54" min.	ASTM D 751-06
Put-up	30 yards	
Repeat	None	
Railroaded	No	
Cleaning Code	W/S	

<u>Performance</u>	<u>Values</u>	<u>Test Method</u>
Grab Tensile	50 lbs./in. x 50 lbs./in. min.	ASTM D 751-06
Trap Tear	15 lbs./in. x 15 lbs./in. min.	ASTM D 751-06
Seam Strength	40 lbs./in. x 40 lbs./in. min.	ASTM D 751-06
Adhesion	4 lbs./in. x 4 lbs./in. min.	ASTM D 751-06
Stretch at 15# MD (warp) x CD (fill)	5% x 10%	ASTM D 751-06
Flex Resistance	25,000 cycles	ASTM D 2097-91
Blocking	No. 1 - Pass	Fed. Std. 191A-TM5872
Crock Resistance	Dry-4; Wet-4	AATCC 8-2013
Wyzenbeek Abrasion	100,000 cycles, #10 Cotton Duck	ASTM D 4157-13
Hydrolysis Resistance	10 weeks	ISO 1419: 1995 E
UV Stability	150 hours	ASTM D 4329-05
Blue Dye Transfer Resistance	Dry 4-5; Wet 4-5	LP-463KC-04-03
Anti-Bacterial	Pass	AATCC 147-2004
Mildew Resistance	Pass	ASTM G-21
Cold Crack	-20°F	CFFA-6A

Flammability

California Bulletin 117-2013, Section 1	Pass
IMO A.652(16)8.2	Pass
U.F.A.C. Class I	Pass
NFPA 260	Pass

Environmental

1. No PVC, Plasticizers, Phthalates, Stabilizers, Heavy Metals or Bisphenol A
2. No chemical flame retardants
3. Does not contain PFAS, PFOA or formaldehyde.
4. 99% of solvents recaptured and recycled



Suitable Applications: Hospitality, Contract, Healthcare, Residential