



MITCHELL

Product Specifications

ReCast® - JAMES



<u>Technical Specs</u>	<u>Values</u>	<u>Test Method</u>
Surface Composition	100% Polyurethane	
Backing Composition	60% leather / 40% polyester	ASTM D 751-06
Finished Width	54" min.	ASTM D 751-06
Repeat	None	
Railroaded	No	
Put-up	30 yards	
Cleaning Code	W	

<u>Performance</u>	<u>Values</u>	<u>Test Method</u>
Grab Tensile	100 lbs./in. x 80 lbs./in. min.	ASTM D 751-06
Trap Tear	18 lbs./in. x 15 lbs./in. min.	ASTM D 5733-99
Seam Strength	65 lbs./in. x 65 lbs./in. min.	ASTM D 751-06
Adhesion	4 lbs./in. x 4 lbs./in. min.	ASTM D 751-06
Stretch at 15# MD (warp) x CD (fill)	2% x 7%	ASTM D 751-06
Blocking	No. 1 - Pass	Fed. Std. 191 A, 5872
Crock Resistance	Dry-4; Wet-4	AATCC 8-2005
Wyzenbeek Abrasion	100,000 cycles, #10 Cotton Duck	ASTM D 4157-02
Hydrolysis Resistance	5 weeks	ASTM D 3690-02
UV Stability	40 hours (no color change)	ASTM D 4329-05

<u>Flammability</u>	
California Bulletin 117-2013, Section 1	Pass
U.F.A.C. Class I	Pass
NFPA 260 Class 1	Pass

Suitable Applications: Commercial; Residential