



## Product Specifications

# ReCast® - TAOS



<u>Technical Specs</u>	<u>Values</u>	<u>Test Method</u>
Surface Composition	100% Polyurethane	
Finished Width	54" min.	ASTM D 751-06
Backing Composition	14% Cotton /28% Leather / 57% Polyester	ASTM D 751-06
Repeat	None	
Railroaded	N	
Put-up	30 yards	
Cleaning Code	W	
<u>Performance</u>	<u>Values</u>	<u>Test Method</u>
Grab Tensile	80 lbs./in. x 60 lbs./in. min.	ASTM D 751-06
Trap Tear	15 lbs./in. x 15 lbs./in. min.	ASTM D 5733-99
Seam Strength	40 lbs./in. x 40 lbs./in. min.	ASTM D 751-06
Adhesion	4 lbs./in. x 4 lbs./in. min.	ASTM D 751-06
Stretch at 15# MD (warp) xCD (fill)	5% x 10%	ASTM D 751-06
Flex Resistance	25,000 cycles	ASTM D 2097-91
Blocking	No. 1 - Pass	Fed. Std. 191 A, 5872
Crock Resistance	Dry-4; Wet-4	AATCC 8-2007
Wyzenbeek Abrasion	100,000 cycles, #10 Cotton Duck	ASTM D 4157-13
Hydrolysis Resistance	5 weeks	ASTM D 3690-02
UV Stability	200 hours	CFFA-6A
<u>Flammability</u>		
California Bulletin 117-2013, Section 1	Pass	
U.F.A.C. Class I	Pass	
NFPA 260 Class 1	Pass	

**Suitable Applications:** Commercial; Residential