



Product Specifications

Sta-Kleen® - SCORE



Technical Specs

Surface Composition	100% Polyurethane
Backing Composition	100% Polyester
Finished Width	54" min.
Repeat	None
Railroaded	No
Put-up	30 yards
Cleaning Code	W/S

Test Method

ASTM D 751-89
ASTM D 751-89

Performance

Grab Tensile	80 lbs./in. x 80 lbs./in. min.
Trap Tear	15 lbs./in. x 15 lbs./in. min.
Seam Strength	45 lbs./in. x 35 lbs./in. min.
Adhesion	4 lbs./in. x 4 lbs./in. min.
Stretch at 15# MD (warp) x CD (fill)	2% x 6%
Flex Resistance	25,000 cycles
Blocking	No. 1 - Pass
Crock Resistance	Dry-4; Wet-4
Wyzenbeek Abrasion	300,000 cycles, #10 Cotton Duck
Hydrolysis Resistance	7 weeks
UV Stability	150 hours
Blue Dye Transfer Resistance	Dry-4-5; Wet-4-5
Anti-Bacterial	Pass
Mildew Resistance	Pass

Test Method

ASTM D 5034-09
ASTM D 5587-07
ASTM D 1683-07A
ASTM D 3690-02
ASTM D 751-89
ASTM D 2097-91
Fed. Std. 191 A , 5872
AATCC 8
ASTM D 4157-07
ISO 1419: 1995 E
ASTM D 4329-05
LP-463KC-04-03
AATCC 147-2004
ASTM G-21

Flammability

IMO A.652(16)8.2	Pass
California Bulletin 117-2013, Section 1	Pass
U.F.A.C. Class I	Pass
NFPA 260	Pass

Environmental

Does not contain PFAS,
PFOA or formaldehyde.
RoHS and REACH compliant.



Suitable Applications: Hospitality, Contract, Healthcare, Residential