



Prosecco




Champagne



Camel



Lemon



Ocean



Blue Smoke




Onyx



Silver



Pumice



Spring Mist

Technical Specifications

Technical Specifications	Values	Test Method
Surface Composition	100% Polyurethane	
Backing Composition	100% Polyester	ASTM D 751-06
Finished Width	54" min.	ASTM D 751-06
Repeat	None	
Railroaded	No	
Put-up	30 yards	
Cleaning Code	W/S	

Performance

Performance	Minimum Values	Test Method
Grab Tensile	80 lbs./in. × 80 lbs./in.	ASTM D 751-06
Trap Tear	15 lbs./in. × 15 lbs./in.	ASTM D 751-06
Seam Strength	40 lbs./in. × 35 lbs./in.	ASTM D 751-06
Adhesion	4 lbs./in. × 4 lbs./in	ASTM D 751-06
Stretch @ 15# MD (warp) × CD (fill)	2% × 6%	ASTM D 751-06
Flex Resistance	25,000 cycles	ASTM D 2097-91
Blocking	No. 1 - Pass	FTMS 191A-TM5872
Crock Resistance	Dry-4; Wet-4	AATCC 8-2007
Wyzenbeek Abrasion	300,000 cycles, #10 Cotton Duck	ASTM D 4157-07
Hydrolysis Resistance	5 weeks	ASTM D 3690-02
	7 weeks	ISO 1419: 1995
Colorfastness to Light	150 hours (Grade 4)	ASTM D 4329-05
Blue Dye Transfer Resistance	Dry-4-5; Wet-4-5	LP-463KC-04-03
Anti-Bacterial	Pass	AATCC 147-2004
Mildew Resistance	Pass	ASTM G-21
Cold Crack (#5 roller)	-20°F	CFFA-6A

Flammability

California Bulletin 117-2013, Section 1	Pass
NFPA 260	Pass
UFAC Class	Pass
IMO A.652(16)8.2	Pass
FMVSS/CMVSS #302	Pass

Environmental

Does not contain PFAS, PFOA or formaldehyde.
Does not contain chemical flame retardants.
RoHS and REACH compliant.

Suitable Applications: Hospitality, Contract, Healthcare, Residential

Cleaning and Disinfecting

Remove ordinary dirt and smudges with mild soap and water. A 10:1 ratio of water to bleach solution may be used as a disinfectant. Rinse the surface with clean water after disinfecting. Dry with a soft, lint-free cloth or towel. We recommend that you use Clorox Healthcare products VersaSure wipes and Hydrogen Peroxide wipes to disinfect Sta-Kleen Performance products in commercial settings.



Sta-Kleen Performance is a compatibility partner with Clorox Healthcare.

