







Construction	Valu	es		Test Method
Surface Composition	100% Polyurethane			
Backing Composition	100% Polyester			ASTM D 751-89
Finished Width	54" min.			ASTM D 751-89
Repeat	None			
Railroaded	No			
Put-up	30 yards			
Cleaning Code	W/S			
Performance	Minimum Values			Test Method
Grab Tensile	80 lbs./in.× 70 lbs./in. min.			ASTM D 5034-09
Trap Tear	15 lbs./in. × 15 lbs./in. min.			ASTM D 5587-07
Seam Strength	60 lbs./in. × 60 lbs./in. min.			ASTM D 1683-07A
Adhesion	4 lbs./in. × 4 lbs./in. min.			ASTM D 751-89
Stretch @ 15# (MD×CD)	2 % ×7%			ASTM D 751-89
Flex Resistance	50,000 cycles			ASTM D 2097-03
Blocking	No. 1 - Pass			Fed. Std. 191 A , 5872
Crock Resistance	Dry-4; Wet-4			AATCC 8-2013
Wyzenbeek Abrasion	100,000 cycles, #10 Cotton Duck			ASTM D 4157-07
Hydrolysis Resistance	10 weeks			ISO 1419: 1995 E
UV Stability	200 hours			AATCC 16-2004
Blue Dye Transfer Resistance	Dry-4-5; Wet-4-5			LP-463KC-04-03
Anti-Bacterial	No growth			AATCC 147-2004
Mildew Resistance	No growth			ASTM G-21
Flammability			Environmental	
California Technical Bulletin 117-2013, Sec. 1 Pass			1. No anti-microbial additives	
IMO A.652(16)8.2 Pass			2. Does not contain PFAS, PFOA	
NFPA 260 Pass			3. Prop 65 compliant	
U.F.A.C. Class I Pass			4. No chemical flame retardants, CA AB2998 compliant	

<u>Suitable Applications</u> Contract, Healthcare, Hospitality, Residential

Cleaning and Disinfecting

Remove ordinary dirt and smudges with mild soap and water. A 10:1 ratio of water to bleach solution may be used as a disinfectant. Rinse the surface with clean water after disinfecting. Dry with a soft, lint-free cloth or towel. We recommend that you use Clorox Healthcare and Clorox Pro products to disinfect Mitchell products in commercial settings.

5. REACH, RoHS, and LEED compliant



