



Product Specifications

Sta-Kleen - TIP TOP



Technical Specs

Surface Composition
Backing Composition
Finished Width
Repeat
Railroaded
Put-up
Cleaning Code

Values

100% Polyurethane
70% Polyester / 30% Leather
54" min.
None
No
30 yards
W/S

Test Method

ASTM D 751-89
ASTM D 751-89

Performance

Grab Tensile
Trap Tear
Seam Strength
Adhesion
Stretch @15# MD (warp) x CD (fill)
Flex Resistance
Blocking
Crock Resistance
Wyzenbeek Abrasion
Hydrolysis Resistance
Colorfastness to Light
Blue Dye Transfer Resistance
Anti-Bacterial
Mildew Resistance

Values

100 lbs./in.x 80 lbs./in. min.
18 lbs./in. x 15 lbs./in. min.
65 lbs./in. x 65 lbs./in.
4 lbs./in. x 4 lbs./in. min.
2% x 7%
25,000 cycles
No. 1 Pass
Dry-4; Wet-4
100,000 cycles, #10 Cotton Duck
7 weeks
150 hours
Dry-4-5; Wet-4-5
Pass
Pass

Test Method

ASTM D 751-06
ASTM D 5733-99
ASTM D 751-06
ASTM D 751-06
ASTM D 751-89
ASTM D 2097-03-02
Fed. Std. 191 A , 5872
AATCC 8
ASTM D 4157-02
ISO 1419: 1995 E
ASTM D 4329
LP-463KC-04-03
AATCC 147-2004
ASTM G-21

Flammability

California Bulletin 117-2013, Section 1
U.F.A.C. Class I
NFPA 260
FMVSS 302
IMO A.652(16)8.2

Pass
Pass
Pass
Pass
Pass

Environmental

Does not contain PFAS, PFOA or formaldehyde.



Suitable Applications: Hospitality, Contact, Healthcare, Residential