



## Product Specifications

# Mitchell Collection - CHAPARRO



<u>Technical Specs</u>	<u>Values</u>	<u>Test Method</u>
Surface Composition	100% Polyurethane	
Finished Width	54" min.	ASTM D 751-06
Weight at 54 inches	24.6 oz./yd $\pm 10\%$	ASTM D 751-06
Thickness	1.7 mm $\pm 10\%$	ASTM D 751-06
Total Weight	16.4 oz./yd <sup>2</sup> $\pm 10\%$	ASTM D 751-06
Backing Composition	100% Polyester	ASTM D 751-06
Backing Weight	3.8 oz./yd <sup>2</sup> $\pm 10\%$	ASTM D 751-06
Repeat	None	
Railroaded	No	
Put-up	30 yards	
Cleaning Code	W	
<u>Performance</u>	<u>Values</u>	<u>Test Method</u>
Grab Tensile	220 lbs./in. x 80 lbs./in. min.	ASTM D 5034-09
Trap Tear	60 lbs./in. x 35 lbs./in. min.	ASTM D 5587-07
Seam Strength	130 lbs./in. x 80 lbs./in. min.	ASTM D 1683-11a
Adhesion	3 lbs./in. x 3 lbs./in. min.	ASTM D 751-06
Stretch @ 15# (MD x CD)	2% x 5%	ASTM D 751-06
Flex Resistance	25,000 Cycles	ASTM D 2097-03(2010)
Blocking	No. 1 - Pass	FTMS 191A-TM5872
Crock Resistance	20 cycles - Pass	AATCC 8-2007
Wyzenbeek Abrasion	50,000 cycles, #10 Cotton Duck	ASTM D 4157-13
Hydrolysis Resistance	5 weeks, no delamination	ASTM D 3690-02
UV Stability	40 hours (no color change)	ASTM D 4329-05
<u>Flammability</u>		
California Bulletin 117-2013, Section 1	Pass	
U.F.A.C. - Class I	Pass	
NFPA 260	Pass	

**Suitable Applications:** Residential

**Country of Origin:** China

01/22/2015 - Revision: 2