



## Product Specifications

# Mitchell Collection - DUNDEE



<u>Technical Specs</u>	<u>Values</u>	<u>Test Method</u>
Surface Composition	100% PVC	
Finished Width	54" min.	ASTM D 751-06
Weight at 54 inches	25.5 oz/yd	ASTM D 751-06
Thickness	1.0 mm $\pm$ 10%	ASTM D 751-06
Total Weight	17.0 oz./yd <sup>2</sup> $\pm$ 10%	ASTM D 751-06
Backing Composition	100% Polyester	ASTM D 751-06
Backing Weight	4.0 oz / yd <sup>2</sup>	ASTM D 751-06
Repeat	V-10.0" / H-13.0"	
Cleaning Code	W	
Put-up	30 yards	
Railroaded	N	
<u>Performance</u>	<u>Values</u>	<u>Test Method</u>
Grab Tensile	80 lbs./in. x 80 lbs./in. min.	ASTM D 751-06
Trap Tear	17 lbs./in. x 14 lbs./in. min.	ASTM D 751-06
Seam Strength	75 lbs./in. x 80 lbs./in. min.	ASTM D 751-06
Adhesion	4 lbs./in. x 4 lbs./in. min.	ASTM D 751-06
Stretch @ 15# (MDxCD)	2% x 7%	ASTM D 751-06
Flex Resistance	25,000 Cycles	ASTM D 2097-03(2010)
Blocking	No. 1 - Pass	FTMS 191A-TM5872
Wyzenbeek Abrasion	30,000 cycles - Pass	ASTM D 4157-10
UV Stability	40 hours (no color change)	ASTM D 4329-05
<u>Flammability</u>		
California Bulletin 117-2013, Section 1	Pass	

**Suitable Applications:** Residential

**Country of Origin:** China

**08/24/2017 - Revision: 3**