



## Product Specifications

# Mitchell Collection - GRANT PARK



<u>Technical</u>	<u>Values</u>	<u>Test Method</u>
Surface Composition	100%PVC	
Finished Width	54" min.	ASTM D 751-06
Weight at 54 inches	30.0 oz./yd.	ASTM D 751-06
Thickness	1.0 mm $\pm$ 10%	ASTM D 751-06
Total Weight	20 oz./yd <sup>2</sup> $\pm$ 10%	ASTM D 751-06
Backing Composition	70% Polyester / 30% Cotton	ASTM D 751-06
Backing Weight	3.5 oz. / yd <sup>2</sup>	ASTM D 751-06
Repeat	None	
Railroaded	No	
Put-up	30 yards	
Cleaning Code	W	
<u>Performance</u>	<u>Values</u>	<u>Test Method</u>
Grab Tensile	85 lbs./in. x 90 lbs./in. min.	ASTM D 751-06
Trap Tear	15 lbs./in. x 15lbs./in. min.	ASTM D 751-06
Seam Strength	65 lbs./in. x 65 lbs./in. min.	ASTM D 751-06
Adhesion	4 lbs./in. x 4 lbs./in. min.	ASTM D 751-06
Stretch @ 15# (MDxCD)	2% x 9%	ASTM D 751-06
Flex Resistance	25,000 Cycles	ASTM D 2097-03(2010)
Blocking	No. 1 - Pass	FTMS 191A-TM5872
Crock Resistance	20 cycles - Pass	AATCC 8-2007
Wyzenbeek Abrasion	100,000 cycles, #10 cotton duck	ASTM D 4157-92
UV Stability	40 hours (no color change)	ASTM D 4329-05
<u>Flammability</u>		<u>Environmental</u>
California Bulletin 117-2013, Section 1	Pass	7p Free - Does not contains the following phthalates: DBP, BBP, DEHP, DOP, DNOP, DINP, DIDP
U.F.A.C. Class I	Pass	
NFPA 260	Pass	

**Suitable Applications:** Residential

**Country of Origin:** China

01/27/2016 - Revision: 5