



## Product Specifications

# Mitchell Collection - HANCOCK



### Technical Specs

<u>Technical Specs</u>	<u>Values</u>	<u>Test Method</u>
Surface Composition	100% Polyurethane	
Finished Width	54" min.	ASTM D 751-89
Weight at 54 inches	23.0 oz./yd.	ASTM D 751-89
Thickness	1.4 mm ±10%	ASTM D 751-89
Total Weight	15.3 oz./yd <sup>2</sup> ±10%	ASTM D 751-89
Backing Composition	95% Polyester, 5% Cotton	ASTM D 751-89
Backing Weight	8.2 oz. / yd <sup>2</sup>	ASTM D 751-89
Put-up	30 yards	
Repeat	None	
Cleaning Code	W	
Railroaded	No	

### Performance

<u>Performance</u>	<u>Values</u>	<u>Test Method</u>
Grab Tensile	100 lbs./in. × 100 lbs./in. min.	ASTM D 5034-09
Trap Tear	15 lbs./in. × 15 lbs./in. min.	ASTM D 5587-07
Seam Strength	35 lbs./in. × 35 lbs./in. min.	ASTM D 1683-07A
Adhesion	3 lbs./in. × 3 lbs./in. min.	ASTM D 751-89
Flex Resistance	25,000 cycles	ASTM D 2097-91
Blocking	No. 1 - Pass	Fed. Std. 191 A , 5872
Wyzenbeek Abrasion	25,000 cycles, #10 Cotton Duck	ASTM D 4157-07
Hydrolysis Resistance	10 days - No delamination	ASTM D 3690-02
UV Stability	40 hours (Grade 4)	AATCC 16-2004
Crock Resistance	20 cycles - Pass	Fed. Std. 191 A , 5651
Stretch at 15# MD (warp) ×CD (fill)	2 % × 2 %	ASTM D 751-89

### Flammability

California Bulletin 117-2013, Section 1	Pass
U.F.A.C. Class I	Pass
NFPA 260	Pass

**Suitable Applications:** Residential

**Country of Origin:** China

**Date:** 12/08/2014 - Revision 1