



## Product Specifications

# Mitchell Collection - LENOX



### Technical Specs

<u>Technical Specs</u>	<u>Values</u>	<u>Test Method</u>
Surface Composition	Polyurethane	
Finished Width	54" min.	ASTM D 751-06
Weight at 54 inches	26.8 oz/yd	ASTM D 751-06
Thickness	1.0 mm ±10%	ASTM D 751-06
Total Weight	17.8 oz./yd <sup>2</sup> ±10%	ASTM D 751-06
Backing Composition	100% Polyester	ASTM D 751-06
Backing Weight	4 oz / yd <sup>2</sup>	ASTM D 751-06
Repeat	None	ASTM D 751-06
Railroaded	No	
Put-up	40 yards	
Cleaning Code	W	

### Performance

<u>Performance</u>	<u>Values</u>	<u>Test Method</u>
Grab Tensile	65 lbs./in. × 85 lbs./in. min.	ASTM D 751-06
Trap Tear	12 lbs./in. × 14 lbs./in. min.	ASTM D 751-06
Seam Strength	65 lbs./in. × 70 lbs./in. min.	ASTM D 751-06
Adhesion	4 lbs./in. × 4 lbs./in. min.	ASTM D 751-06
Stretch @ 15# (MD×CD)	5%× 5%	ASTM D 751-06
Flex Resistance	25,000 Cycles	ASTM D 2097-03(2010)
Blocking	No. 1 - Pass	FTMS 191A-TM5872
Crock Resistance	20 cycles - Pass	AATCC 8-2007
Hydrolysis Resistance	10 days - No delamination	ASTM D 3690-02
Wyzenbeek Abrasion	100,000 cycles, #10 cotton duck	ASTM D 4157-10
UV Stability	40 hours (no color change)	ASTM D 4329-05

### Flammability

FMVSS302	Pass
California Bulletin 117-2013, Section 1	Pass
U.F.A.C. Class I	Pass
NFPA 260	Pass

**Suitable Applications:** Residential

**Country of Origin:** China

01/05/2016 - Revision: 2