



## Product Specifications

# Mitchell Collection - LIZARDO



### Technical Specs

	<u>Values</u>	<u>Test Method</u>
Surface Composition	100% PU	
Finished Width	54" min.	ASTM D 751-06
Weight at 54 inches	21.5 oz/yd	ASTM D 751-06
Thickness	1.0 mm $\pm$ 10%	ASTM D 751-06
Total Weight	14.3 oz./yd <sup>2</sup> $\pm$ 10%	ASTM D 751-06
Backing Composition	65% Polyester / 35% Cotton	ASTM D 751-06
Backing Weight	4.0 oz / yd <sup>2</sup> $\pm$ 10%	ASTM D 751-06
Repeat	V: 9" / H: 8"	ASTM D 751-06
Railroaded	N	
Put-up	40 yards	
Cleaning Code	W	

### Performance

	<u>Values</u>	<u>Test Method</u>
Grab Tensile	80 lbs./in. $\times$ 90 lbs./in. min.	ASTM D 751-06
Trap Tear	15 lbs./in. $\times$ 12lbs./in. min.	ASTM D 751-06
Seam Strength	60 lbs./in. $\times$ 60 lbs./in. min.	ASTM D 751-06
Adhesion	4 lbs./in. $\times$ 4 lbs./in. min.	ASTM D 751-06
Stretch @ 15# (MD $\times$ CD)	2% $\times$ 12%	ASTM D 751-06
Flex Resistance	25,000 Cycles	ASTM D 2097-03(2010)
Blocking	No. 1 - Pass	FTMS 191A-TM5872
Crock Resistance	Dry-4; Wet-4	AATCC 8-2007
Wyzenbeek Abrasion	100,000 cycles, Wire Screen	ASTM D 4157-92
Hydrolysis Resistance	5 weeks, no delamination	ASTM D 3690-02
UV Stability	40 hours (no color change)	ASTM D 4329-05

### Flammability

California Bulletin 117-2013, Section 1	Pass
U.F.A.C. Class I	Pass
NFPA 260	Pass

**Suitable Applications:** Commercial

**Country of Origin:** China

02/17/2015 - Revision: 5