



Product Specifications

Mitchell Collection - MAGIC



Technical Specs

<u>Technical Specs</u>	<u>Values</u>	<u>Test Method</u>
Top Finish	Polyurethane - 5%	ASTM D 751-06
Surface Composition	PVC Foam - 70%	ASTM D 751-06
Backing Composition	Polyester - 25%	ASTM D 751-06
Finished Width	54" min.	ASTM D 751-06
Weight at 54 inches	31 oz./yd. ±10%	ASTM D 751-06
Thickness	1.1 mm ±10%	ASTM D 751-06
Total Weight	21 oz./yd ² ±10%	ASTM D 751-06
Backing Composition	100% Polyester	ASTM D 751-06
Backing Weight	5.3 oz. / yd ²	ASTM D 751-06
Repeat	None	ASTM D 751-06
Railroaded	No	
Put-up	30 yards	
Cleaning Code	W	

Performance

<u>Performance</u>	<u>Values</u>	<u>Test Method</u>
Grab Tensile	80 lbs./in. × 60 lbs./in. min.	ASTM D 751-06
Trap Tear	18 lbs./in. × 18 lbs./in. min.	ASTM D 751-06
Seam Strength	35 lbs./in. × 35 lbs./in. min.	ASTM D 751-06
Adhesion	3 lbs./in. × 3 lbs./in. min.	ASTM D 751-06
Flex Resistance	25,000 Cycles	ASTM D 2097-91
Blocking	No. 1 - Pass	FTMS 191A-TM5872
Wyzenbeek Abrasion	80,000 cycles, #10 cotton duck	ASTM D 4157-13
Hydrolysis Resistance	5 weeks	ISO 1419: 1995
UV Stability	150 hours	ASTM D 4329-05
Crock Resistance	Dry-4; Wet-4	AATCC 8-2007
Stretch (MD×CD)	2% × 6% at 15 lbs.	ASTM D 751-06

Flammability

California Bulletin 117-2013, Section 1	Pass
NFPA 260	Pass
UFAC Class I	Pass
FMVSS/CMVSS #302	Pass

Environmental

Does not contain any flame retardant chemicals.

Cleaning

Do not use chemical cleaners.
Mild soap and water only.

Suitable Applications: Hospitality

Country of Origin: China

12/12/2018 - Revision: 6