



Product Specifications

Mitchell Collection - SIERRA



<u>Technical Specs</u>	<u>Values</u>	<u>Test Method</u>
Surface Composition	100% PU	
Finished Width	54" min.	ASTM D 751-06
Weight at 54 inches	19.5 oz/yd	ASTM D 751-06
Thickness	1.1 mm ±10%	ASTM D 751-06
Total Weight	13 oz./yd ² ±10%	ASTM D 751-06
Backing Composition	65% Polyester / 35% Cotton	ASTM D 751-06
Backing Weight	4.6 oz / yd ² ±10%	ASTM D 751-06
Repeat	None	
Railroaded	No	
Put-up	30 yards	
Cleaning Code	W	
<u>Performance</u>	<u>Values</u>	<u>Test Method</u>
Grab Tensile	80 lbs./in. × 70 lbs./in. min.	ASTM D 751-06
Trap Tear	15 lbs./in. × 12lbs./in. min.	ASTM D 751-06
Seam Strength	60 lbs./in. × 60 lbs./in. min.	ASTM D 751-06
Adhesion	3 lbs./in. × 3 lbs./in. min.	ASTM D 751-06
Stretch @ 15# (MD×CD)	3% × 4%	ASTM D 751-06
Flex Resistance	25,000 Cycles	ASTM D 2097-03(2010)
Blocking	No. 1 - Pass	FTMS 191A-TM5872
Crock Resistance	Dry-4; Wet-4	AATCC 8-2007
Wyzenbeek Abrasion	100,000 cycles, #8 cotton duck	ASTM D 4157-92
Hydrolysis Resistance	3 weeks	ISO 5423: 1992cE
UV Stability	40 hours (no color change)	ASTM D 4329-05
<u>Flammability</u>		
California Bulletin 117-2013, Section 1	Pass	
U.F.A.C. Class I	Pass	
NFPA 260	Pass	

Suitable Applications: Residential

Country of Origin: China

02/04/2018 - Revision: 3