



## Product Specifications

# Mitchell Collection - TETON



<u>Technical Specs</u>	<u>Values</u>	<u>Test Method</u>
Surface Composition	Polyurethane	
Finished Width	54" min.	ASTM D 751-06
Weight at 54 inches	20.2 oz/yd	ASTM D 751-06
Thickness	1.0 mm ±10%	ASTM D 751-06
Total Weight	13.5 oz./yd <sup>2</sup> ±10%	ASTM D 751-06
Backing Composition	65% Polyester / 35% Cotton	ASTM D 751-06
Backing Weight	4.0 oz / yd <sup>2</sup>	ASTM D 751-06
Repeat	None	
Railroaded	No	
Put-up	30 yards	
Cleaning Code	W	
<u>Performance</u>	<u>Values</u>	<u>Test Method</u>
Grab Tensile	80 lbs./in. x 70 lbs./in. min.	ASTM D 751-06
Trap Tear	15 lbs./in. x 12lbs./in. min.	ASTM D 751-06
Seam Strength	60 lbs./in. x 60 lbs./in. min.	ASTM D 751-06
Adhesion	4 lbs./in. x 4 lbs./in. min.	ASTM D 751-06
Stretch @15# (MD×CD)	2% x 7%	ASTM D 751-06
Flex Resistance	25,000 Cycles	ASTM D 2097-03(2010)
Blocking	No. 1 - Pass	FTMS 191A-TM5872
Crock Resistance	20 cycles - Pass	AATCC 8-2007
Wyzenbeek Abrasion	100,000 cycles, #8 cotton duck	ASTM D 4157-92
UV Stability	40 hours (no color change)	ASTM D 4329-05
<u>Flammability</u>	<u>Values</u>	
California Bulletin 117-2013, Section 1	Pass	
U.F.A.C. Class I	Pass	
NFPA 260	Pass	

**Suitable Applications:** Residential

**Country of Origin:** China

**11/26/2014 - Revision: 1**