



Product Specifications

ReCast® - JAMES



<u>Technical Specs</u>	<u>Values</u>	<u>Test Method</u>
Surface Composition	100% Polyurethane	
Finished Width	54" min.	ASTM D 751-06
Weight at 54 inches	25.6 oz./yd.	ASTM D 751-06
Thickness	1.3 mm ±10%	ASTM D 751-06
Total Weight	17 oz./yd ² ±10%	ASTM D 751-06
Backing Composition	60% leather / 40% polyester	ASTM D 751-06
Backing Weight	7.3 oz. / yd ² ±10%	ASTM D 751-06
Repeat	None	
Railroaded	No	
Put-up	30 yards	
Cleaning Code	W	
<u>Performance</u>	<u>Values</u>	<u>Test Method</u>
Grab Tensile	100 lbs./in. × 80 lbs./in. min.	ASTM D 751-06
Trap Tear	18 lbs./in. × 15 lbs./in. min.	ASTM D 5733-99
Seam Strength	65 lbs./in. × 65 lbs./in. min.	ASTM D 751-06
Adhesion	4 lbs./in. × 4 lbs./in. min.	ASTM D 751-06
Stretch at 15# MD (warp) ×CD (fill)	2% × 7%	ASTM D 751-06
Blocking	No. 1 - Pass	Fed. Std. 191 A, 5872
Crock Resistance	Dry-4; Wet-4	AATCC 8-2005
Wyzenbeek Abrasion	100,000 cycles, #10 Cotton Duck	ASTM D 4157-02
Hydrolysis Resistance	5 weeks	ASTM D 3690-02
UV Stability	40 hours (no color change)	ASTM D 4329-05
<u>Flammability</u>		
California Bulletin 117-2013, Section 1	Pass	
U.F.A.C. Class I	Pass	
NFPA 260 Class 1	Pass	

Suitable Applications: Commercial; Residential

Country of Origin: China

10/16/2015 - Revision: 7